



PARSHWANATH GROUP OF INDUSTRIES

Plot No. I - 5617, Phase - 2, Vatva, G.I.D.C.
Ahmedabad - 382445, Gujarat, India

Telephone : +(91)-(79)-40083231/40085401/40085400

Email : inquiry@parshwadyes.com

Reactive Vinyl Sulphone Base Dye	FASTNESS PROPERTIES				
	Light	Washing	Perspiration	Hypochlorite	Dischargeability
Reactive Red 4B Reactive Red - 24	6	3-4	5	1	G
Reactive Red 5B Reactive Red - 35	6	3-4	5	1	G
Reactive Red C2G Reactive Red - 106	4	4-5	5	1	G
Reactive Red RB Reactive Red - 198	5-6	4-5	4	1	F
Reactive Orange 3R Reactive Orange - 16	5-6	5	5	1	G
Reactive Orange 2R Reactive Orange - 7	4-5	4-5	5	1-2	G
Reactive G. Yellow R Reactive Yellow - 20	5	4-5	5	1	G
Reactive Yellow FG Reactive Yellow 42	5	5	5	1	G
Reactive Yellow GR Reactive Yellow - 15	6	5	5	1	G
Reactive Yellow RTN Reactive Yellow - 24	6-7	4	4	2	F
Reactive G. Yellow RNL Reactive G. Yellow - 107	5	4-5	4-5	1	G
Reactive Yellow R Reactive Yellow - 77	4-5	5	5	1	G
Reactive Yellow GL Reactive Yellow - 37	6-7	4-5	5	1	G
Reactive Black B Reactive Black -5	5	4-5	5	1	G
Reactive Black RL Reactive Black - 31	7	4-5	5	3-4	F
Reactive Violet 5R Reactive Violet - 5	6-7	4	3-4	5	P
Reactive Tur. Blue G. (133% & 160%) Reactive Blue-21	6	4-5	5	3-4	P
Reactive Tur. Blue H2GP	6	4	5	3-4	P
Reactive Blue 3R Reactive Blue - 28	7	4	5	3-4	G
Reactive Blue R Reactive Blue - 19	6-7	4-5	4-5	3-4	F
Reactive Blue RGB Reactive Blue - 250	4-5	3-4	4	1	G
Reactive Blue BB Reactive Blue - 220	6-7	4	5	1	G
Reactive Dark Blue HR Reactive Blue - 89	5-6	3-4	5	1	F
Reactive Navy Blue GG Reactive Blue - 203	4-5	3-4	5	1	F
Reactive Navy Blue GG Reactive Blue - 203A	-	-	-	-	-
Reactive Brown GR Reactive Brown - 18	6	4-5	4	1	G
Reactive Black-N150 Reactive Black-N200	5	4-5	5	1	G